



Formosa Plastics®

Formolene® PP

Formolene® 2610A

Impact Copolymer for Compounding and Injection Molded Applications

Formolene® 2610A is a high impact copolymer of polypropylene designed for such applications as Automotive Compounds and injection molding of Lawn & Garden products and Appliances. It is characterized by its easy mold flow, excellent physical property balance of stiffness and impact at room temperature and sub ambient conditions as well as finished product dimensional stability.

Formolene® 2610A complies with the U. S. Food and Drug Administration regulation 21 CFR 177.1520(c)(3.4). This material may only be used in contact with foods of type I, II, III, IV-B, VI, VII, VIII and IX as described in Table 1 of 21 CFR 176.170(c)

Typical Properties of this Commercial Grade

Melt Flow Rate, I ₂ @ 230°C, g/10 min	ASTM D1238	10.0
Density, g/cm ³	ASTM D1505	0.9
Tensile Strength at Yield (50 mm/min), psi	ASTM D638	2,950
Elongation at Yield (50 mm/min), %	ASTM D638	6
Flexural Modulus (1.3 mm/min), 1% Secant, psi	ASTM D790	140,000
Rockwell Hardness, R Scale	ASTM D785	105
Notched Izod Impact Strength @ 73°F, ft-lb/in	ASTM D256	11
Notched Izod Impact Strength @ -18°C, ft-lb/in	ASTM D256	1.9
Notched Izod Impact Strength @ -30°C, ft-lb/in	ASTM D256	1.7
Heat Deflection Temperature @ 66 psi, °C	ASTM D648	86
Heat Deflection Temperature @ 264 psi, °C	ASTM D648	50

Notes: Specimens were injection molded according to the conditions specified in ASTM D4101.

Published 3/99, Revised 08/10

*FM 46020 applies to specific copolymers

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® is a registered trademark of FPC USA



ISO 9001:2008
FS 70459
FM 31429
FM 46020*



ISO 14001:2004
EMS 35710