

Technical Data Sheet

Petrothene GA574189



Linear Low Density Polyethylene

Product Description

Petrothene GA574189 exhibits excellent flow and impact with good stiffness. Typical applications include lids, closures, containers, housewares and medical items.

Regulatory Status

For regulatory compliance information, see *Petrothene* GA574189 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Caps & Closures; Containers; Housewares; Lids; Outdoor and Power Tools
Market	Rigid Packaging
Processing Method	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	50	g/10 min	50	g/10 min	ASTM D1238
Density, (23 °C)	0.926	g/cm ³	0.926	g/cm ³	ASTM D1505
Spiral Flow	17.9	in	45.4	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	70000	psi	480	MPa	ASTM D790
(2% Secant)	61000	psi	420	MPa	ASTM D790
Tensile Strength at Break, (23 °C)	1300	psi	9	MPa	ASTM D638
Tensile Strength at Yield, (23 °C)	2200	psi	15	MPa	ASTM D638
Tensile Elongation at Yield, (23 °C)	11	%	11	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	60		60		ASTM D2240
Thermal					
Vicat Softening Temperature	184	°F	84	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	-98	°F	-72	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	117	°F	47	°C	ASTM D648

Notes

Tensile properties were run with a crosshead speed of 20 inches/min or 500 mm/min.

Flexural Modulus properties were run with a crosshead speed of 0.5 inches/min or 12.5 mm/min.

Spiral Flow measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.0625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440 °F.

Deflection Temperature Under Load and Low Temperature Brittleness data are for control and development work and are not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.